



E-Z MIX INC.

FINE GROUT

With Grout Additive
SELF-CONSOLIDATING GROUT

PRODUCT

PMP Fine Grout with Grout Additive - Self-Consolidating Grout

DESCRIPTION

PMP Fine Grout with Grout Additive is a dry preblended self-consolidating grout specifically designed to fill masonry block cores without the need of mechanical consolidation when placed.

USES

Grout for:

- Concrete Block
- Cavity Walls
- Around windows and door frames

ADVANTAGES

- Fluid at low water ratio
- Minimum to no shrinkage
- Superior bonding properties
- Cohesive at high fluidity

PACKAGING

Available in 94 lb. paper bags, 3000 lb. bulk bags and bulk. Information on silo and bulk systems available upon request.

COVERAGE

One 94 lb. bag will yield approximately 0.85 – 0.90 cubic feet.

TECHNICAL DATA

PMP Fine Grout with Grout Additive meets ASTM C476 specifications and achieves the following typical properties when tested in accordance with that specification and ASTM C1611:



MIXING

Add approximately 7 quarts of clean water for each 94 lb. bag and mix for a minimum of 5 minutes. Prior to use, a T-50 test must be performed achieving a minimum slump flow of 20" in 5 seconds or less. If additional water is needed, add sparingly until the desired slump flow range of 24"- 30" is achieved, when tested in accordance with ASTM C1611. Do not over water as this will have a negative effect on strength.

LIMITATIONS

Do not apply when temperature is below or may fall below 40° F prior to curing.

WARRANTY

The technical information and usage statement are based on our best knowledge. The content of this specification sheet is presented for information purposes only and do not constitute responsibility for their use. The manufacturer will replace only that material which is proven defective due to quality of the components of the manufacturing process.

CAUTION

Prolonged exposure to dust may cause delayed lung disease. Eliminate exposure to dust. Use NIOSH approved mask for silica dust. Freshly mixed material may cause skin irritation. Avoid direct contact when possible and wash exposed skin areas promptly with water and get prompt medical attention. See Safety Data Sheet.

TABLE 1 TYPICAL PHYSICAL PROPERTIES

Property	Results
T50	< 5 seconds
Slump Flow	24-30 "
Visual Stability Index	0 or 1
28 day Strength	3,000 psi (minimum)

For technical support contact:

www.ezmixinc.com jjara@ezmixinc.com

Corporate Office:
11374 Tuxford St.
Sun Valley, CA 91352
(818) 767-8576

Rialto Plant:
3355 Industrial Drive.
Rialto, CA 92316
(909) 874-7686

Sun Valley Plant:
11450 Tuxford St.
Sun Valley, CA 91352
(818) 768-0568



WARNING: This product can expose you to chemicals including Chromium (hexavalent compounds), which are known to the state of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.